

CONTRACTOR GRADE FOR RESIDENTIAL AND COMMERCIAL PROJECTS

#### **USES:**

Ideal for shaded areas, pool decks, outdoor showers and other areas where mildew, fungus and algae are a concern. Suitable for concrete and clay pavers, flat and stamped concrete, or natural and manufactured stone. Also suitable for masonry, retaining walls, porous or unglazed tile and terrazzo. Recommended for high traffic areas where high durability and superior chemical resistance is desired. Not recommended for marble, granite, ceramic tile or porcelain.

#### PRODUCT DESCRIPTION:

SB-6750 SurfacePRO Premium is a proprietary two-part water reducible, clear, aliphatic urethane sealer and joint sand stabilizer. **SB-6750** is specially formulated with an antifungal designed to help inhibit the growth of mold, moss and algae on the sealer film when applied to horizontal or vertical surfaces. **SB-6750** is a multi-use product: it deeply enhances with a gloss finish producing a luxurious wet look; provides great surface protection and joint sand stabilization. This product can be used inside and outside on old and new surfaces. Optimal results when performing same day cleaning, sanding and sealing with SB-6750, can be achieved when following the recommended application process. SB-6750 provides a non-yellowing protective layer on the surface that is extremely durable and resistant to mild acid, alkali, chemicals and salt attacks. SB-6750 will increase the stain resistance of the surface and allow easier cleaning, maintenance, and extended wear. On new concrete, mortar, grout or overlays, it is recommended to wait 7 days before applying SB-6750 to allow for curing. SB-6750 is a water-based two component product that reguires mixing and dilution. Once mixed, it has the consistency of water and is milky white when applied and dries clear. Cured sealer is freeze resistant to -60°F (-51°C) and is stable up to a temperature of 180°F (-51°C).

#### RECOMMENDED FOR PROFESSIONAL USE ONLY.

WARNING: Once applied, SB-6750 cannot be chemically stripped

#### PREPARATION:

TEST FIRST on a small inconspicuous area to determine the suitability and if desired results are achievable with this product on your specific surface. (Caution: product is difficult to remove.) The surface should be thoroughly clean and free from oil, dust, loose material and previously applied sealer. Remove and kill growth of any mold, mildew, fungus or algae prior to



application of sealer. If needed, prepare surface with Surebond Cleaners before sealing. When using SB-6750 as a sealer without joint stabilization, it can be applied to a damp surface with no ponding or pooling of water present. For applications with joint stabilization, allow the surface to dry. Cover/protect nearby landscape, vehicles and buildings from overspray during application.

#### **Preparation For Joint Stabilization:**

Surface must be dry for ease of installation. For optimal joint stabilization, the paver joints should be no more than 34" wide and filled with dry correctly graded joint sand that meets the ASTM C144 standard. The top level of the sand should not exceed the bottom of the chamfer or 1/8" below the surface on non-beveled or tumbled paver surfaces. Compaction is recommended after sweeping sand into joints to minimize voids in sand joints. Use a vibratory compactor with neoprene pad or vibratory roller to consolidate the joint sand. A leaf blower is recommended to remove dust, debris and fine particles from the surface before sealing. Do not use wet joint sand because it will severely diminish joint stabilization.

SurfacePRO Sealer Series

from the applied substrate. If removal is necessary, sand-blasting or	Sulfacel No Scale Sches			
other mechanical methods must be used. Use product at own risk.	SB-6715	SB-6725	SB-6750	SB-6700
FEATURES	RTU	CLASSIC	PREMIUM	ULTRA
Joint Sand Stabilization - Reduces Sand Loss	Good	Good	Great	Optimal
Enhancement - Darkens Surface Tone	Good	Good	Deep	Ultra
Sheen - Shine or Luster	Semi-Gloss	Semi-Gloss	Gloss	Gloss
Durability - Long Term Performance	Good	Great	Great	Ultimate
Damp Application (no puddling or pooling)	1	1	✓	✓
Antifungal Film Protection - Inhibits Mold, Moss & Algae	1	1	✓	1
Strippable - Ease of Removal	/			
Ready To Use - No Dilution Required	1		1 1	
Breathable – Does Not Trap Moisture or Efflorescence	1	/	✓	<b>√</b>
Low VOC - Environmentally Friendly, Water Based Formula	/	1	1	1

800-932-3343 www.sek.us.com

### **TECHNICAL DATA SHEET**

## **SB-6750 SurfacePRO Premium**

#### **FULL KIT SB-6750 MIXING INSTRUCTIONS:**

SB-6750 is a two-part product that comes packaged in a kit which contains one five gallon pail with 4 gallons of Part A and one gallon container of Part B.

#### **Tools Needed:**

Variable Speed Drill
 Paddle Mixer

#### **Mixing Instructions:**

Blend the container of **Part B** into the pail of **Part A** with a drill and paddle mixer on low speed for 1-2 minutes. Do not whip air into the mixture.

**Pot Life: SB-6750 Mixture** (combined **Parts A and B**) has a pot life of 90 minutes which varies based on temperature and humidity. Do not mix more material than can be used in a 90 minute period. Do not store **SB-6750 Mixture**. If less than the entire kit is needed, see Project Calculators for more information.

#### SB-6750 DILUTION INSTRUCTIONS:

The SB-6750 Mixture is a super concentrated sealer which requires water dilution dependent on desired sheen and joint stabilization.

#### **Tools Needed:**

Variable Speed Drill
 Paddle Mixer
 One or Two Additional Clean Five Gallon Pails (Quantity varies based on desired dilution.)

Before diluting, use the SB-6750 Marking Label as a guide (found on Part A pail), mark D1 and D2 on all pails.

#### 1:1 Dilution Ratio (D1):

Suitable on all surfaces to create a gloss sheen with great joint sand stabilization. Can also be used as a sealer without joint stabilization.

Yields 10 gallons of ready to use SB-6750.

#### **Full Kit D1 Dilution Instructions:**

- 1. Pour half of the SB-6750 Mixture into one previously marked five gallon pail up to the D1 line. Contents of both pails should be at the D1 line.
- 2. Fill each pail to the top rib (1.5" down from the top of pail) with water.
- 3. Using a drill with paddle mixer, mix on low speed for 1–2 minutes. Do not whip air into the dilution.

## DILUTION 1 (D1) - SB-6750 SurfacePRO Premium Project Coverage Calculator

Total Square	Feet Yield‡	SB-6750 SurfacePRO Premium		Dilution	
Sealing with Joint Stabilization*	Sealing Only**	Part A	Part B	Add Water***	D1 Total Volume
1,000	2,500	4 Gallons Fu	ıll Kit 1 Gallon	5 Gallons	10 Gallons
500	1,250	2 Gallons Ha	alf Kit .50 Gallon	2.5 Gallons	5 Gallons
250	625	1 Gallon	1 Quart (32 oz.)	1.25 Gallons	2.5 Gallons
100	250	.50 Gallon	1 Pint (16 oz.)	.50 Gallon	~1.25 Gallons

<sup>\*</sup> Coverage rate used for joint stabilization - 100 SF per gallon.



<sup>\*\*</sup> Coverage rate used for sealing - 250 SF per gallon.

<sup>\*\*\*</sup> Add water to make total volume

<sup>‡</sup> Single Application. Actual coverage may vary depending on the type, age, condition, joint size and porosity of the surface, application method and site conditions such as temperature.

# SB-6750 SurfacePRO Premium

#### 2:1 Dilution Ratio (D2):

Suitable on all surfaces to create a satin/semi-gloss sheen. Can also be used as a sealer with joint stabilization.

Yields 15 gallons of ready to use SB-6750.

#### **Full Kit D2 Dilution Instructions:**

- 1. Pour approximately a third of the **SB-6750 Mixture** into each of the previously marked two five gallon pails up to the **D2** line. Contents of all three pails should be at the **D2** line.
- 2. Fill each pail to the top rib (1.5" down from the top of pail) with water.
- 3. Using a drill with paddle mixer, mix on low speed for 1-2 minutes. Do not whip air into the dilution.

## DILUTION 2 (D2) - SB-6750 SurfacePRO Premium Project Coverage Calculator

Total Square	Feet Yield‡	SB-6750 SurfacePRO Premium		Dilution	
Sealing with Joint Stabilization*	Sealing Only**	Part A	Part B	Add Water***	D2 Total Volume
1,500	3,750	4 Gallons Fu	<mark>II Kit</mark> 1 Gallon	10 Gallons	15 Gallons
750	1,875	2 Gallons Ha	of Kit .50 Gallon	5 Gallons	7.5 Gallons
375	940	1 Gallon	1 Quart (32 oz.)	2.5 Gallons	3.75 Gallons
150	375	.50 Gallon	1 Pint (16 oz.)	1.25 Gallon	~2 Gallons
100	250	1 Quart	.50 Pint (8 oz.)	2.5 Quarts (80 oz.)	~1 Gallon

<sup>\*</sup> Coverage rate used for joint stabilization - 100 SF per gallon.

#### APPLICATION INFORMATION:

Apply when day and night temperatures are between 45°F - 95°F. To cool hot surfaces, mist with water without ponding or pooling prior to applying SB-6750. Avoid windy conditions to keep sealer spray from drifting. SB-6750 is a two part product: read and follow the Mixing and Dilution Instructions before applying. Use product coverage calculators to determine the amount of material required for the project; material coverage will depend on the surface type and its porosity. Apply SB-6750 after dilution with a low pressure, high volume sprayer such as an airless sprayer or hand held garden sprayer (pump-up). Do not apply too thick to avoid air bubbles in the sealer film. Saturate the surface to ensure proper penetration. Use a squeegee or foam roller to provide uniform coverage over the entire surface area and to remove excess sealer. For exterior applications with joint stabilization, the surface and joints should be flood coated using a low pressure, high volume sprayer following the coverage guidelines. Use a soft foam squeegee to direct excess sealer into the joints. It is recommended to back-roll to even out the sealer on textured or uneven surfaces to eliminate pooling. For optimal performance a second application should be applied. Second coat should be applied as soon as practical after the first application has visually cleared and is dry to the touch, which is usually within one hour. Second application must be applied prior to full cure (see Dry Time for more information). With interior applications, SB-6750 may be carefully sprayed or applied with a slit foam roller taking care not to roll back and forth excessively. NOTE: To minimize slipperiness on travertine, pool decks and very smooth surfaces, use an anti-slip additive with both D1 and D2 applications.

#### **DRY TIME:**

Surface will be dry to the touch in 1-2 hours assuming the air temperature is between 65°F - 85°F at 50% relative humidity. Low surface or air temperature will extend dry time. Protect surface from dust, rain, condensation and traffic while drying. Full cure will take 24–36 hours depending on weather and site conditions. Once surface has visually cleared and dried to the touch, area can be open to foot traffic in 24 hours and vehicular traffic in 48 hours depending on weather and site conditions.

SUREBOND®

<sup>\*\*</sup> Coverage rate used for sealing - 250 SF per gallon.

<sup>\*\*\*</sup> Add water to make total volume

<sup>‡</sup> Single Application. Actual coverage may vary depending on the type, age, condition, joint size and porosity of the surface, application method and site conditions such as temperature.

### TECHNICAL DATA SHEET

## **SB-6750 SurfacePRO Premium**

**CLEAN UP:** For tools and equipment, use soap and water before product is allowed to dry.

MAINTENANCE/RE-APPLICATION: Sealed surfaces should be properly maintained following SEK-Surebond's Restoration and Maintenance System guidelines to get the best long-term performance from both the pavement and SB-6750. Keep surface clear of buildup of dirt, grime and stains by rinsing with cold, clean water. If staining of surface does occur, Surebond sealers are compatible with Surebond multi-use and specialty cleaners which can be used to remove general dirtiness, organic and inorganic stains like oils, food and beverages and mineral deposits from the surface. Test cleaners in inconspicuous area prior to cleaning. Be sure to check dilution rates for all cleaners to determine if they are ready to use or to determine appropriate dilution rate especially for sealed surfaces. Efflorescence should be removed using Efflo Off and a pressure washer, in conjunction with agitation from a natural fiber brush. Care should be taken to ensure that excessive pressure is not utilized, as it may erode joint sand and could damage the surface itself. Thoroughly rinse all cleaner off the surface before sealing.

**SB-6750** re-application may need to be carried out every 2-4 years depending on the type of surface and environmental/site conditions.

#### PACKAGING/SIZES (TWO-PART SYSTEM):

Sold as a kit containing one five gallon pail with 4 gallons of **Part A** and one gallon container of **Part B**.

#### **COVERAGE\*:**

APPLICATION	SQ FEET	SQ METERS
Sealing with joint stabilization	80 - 120	7.4 - 11.1
Sealing without joint stabilization	200 - 300	18.6 - 27.9

<sup>\*</sup>Per gallon once mixed and diluted. Single application. Actual coverage may vary depending on type, age, condition, joint size and porosity of the surface, application method and site conditions such as temperature. For more uniform coverage, a second coat must be applied after the first coat has dried to the touch.

#### STORAGE:

Keep container tightly closed and in a well-ventilated place. Store away from heat. Do not allow to freeze.

#### SHELF LIFE:

1 year from manufacture date when stored in unopened containers (50°F - 80°F)

**POT LIFE:** 90 minutes at 75°F **VOC CONTENT:** < 50 g/L

#### LIMITATIONS:

Protect sealer from freezing and store in a cool place when not in use. In winter, keep in heated area. On new concrete wait a minimum of 7 days, to allow the surface to cure, before sealing. This sealer is not recommended for marble, granite, ceramic tile, porcelain and polished surfaces with a high gloss as they do not absorb the sealer. Recommended for professional use only. Once applied, **SB-6750** cannot be chemically stripped from the applied substrate. If removal is necessary, sand-blasting or other mechanical methods must be used. Use at your own risk. A test area is ALWAYS recommended to determine product suitability and compatibility with your specific surface before use and to verify if desired results are achievable. Due to the inherent variability of natural stone or clay products, long term

performance may vary. Please consult with SEK-Surebond prior to sealing if there are concerns. The use of an anti-slip is recommended for increased traction on surface inclines or around consistently wet areas such as pool deck surrounds. Do not use below grade or where water is always present. A minimum temperature of 40°F (5°C) must be maintained for a period of 24 hours prior to application. Surface temperature should not exceed 120°F (48°C) during application. Work should cease in inclement weather (rain or strong wind.)

#### PRECAUTIONARY INFORMATION:

KEEP OUT OF REACH OF CHILDREN • Use in a well ventilated area • Do not breathe vapors, spray or mist • Wear protective gloves, clothing, face and eye protection • Wash thoroughly after handling (See Safety Data Sheet for complete information.)

#### **EMERGENCY & FIRST AID MEASURES:**

If swallowed: Call a POISON CENTER or physician if you feel unwell. If on skin: Wash with plenty of soap and water. Get medical attention if irritation occurs. Take off contaminated clothing and wash before reuse. If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Get medical attention if eye irritation persists. If inhaled: Remove person to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or physician if you feel unwell. In case of fire: Use water, water fog, dry chemical CO2 or alcohol resistant foam to extinguish. (See Safety Data Sheet for complete information.)

#### **WARRANTY:**

SEK-Surebond warrants its products to substantially conform to its published specifications at the time of purchase. The foregoing is the sole limited warranty applicable to the products. SEK-SUREBOND HEREBY DISCLAIMS ALL OTHER WARRANTIES OF ANY KIND OR NATURE, WHETHER EXPRESS, IMPLIED, OR STATUTORY, INCLUDING WITHOUT LIMITATION THE IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE. OR ANY OTHER WARRANTY OTHER THAN THE WARRANTY SET FORTH ABOVE. The user is solely responsible for determining suitability of the products for their particular use. While the actual application of this product is out of the control of SEK-Surebond, it is recommended that the application guidelines be followed completely and accurately. SEK-Surebond's liability for any damage shall not exceed the purchase price of the product used, and it shall have no liability for consequential, incidental or punitive damages.



3925 Stern Ave. St. Charles, IL 60174 Email: info@sek.us.com Fax: 630-762-0607

800-932-3343 www.sek.us.com

