SB-6000 APPLICATION INSTRUCTIONS



Page 1

SUITABLE SURFACES:

Concrete and clay pavers, flat and stamped concrete, masonry, natural and manufactured stone, segmental retaining wall blocks, concrete walls and exposed aggregate. May be used on porous or unglazed tile, terrazzo and terra cotta. Not recommended for granite, marble, asphalt, glazed or ceramic tile. Due to the inherent variability of natural stone and clay products, long term performance may vary. Please consult with SEK-Surebond prior to sealing if there are concerns.

PREPARATION:

TEST SEALER FIRST on a small inconspicuous area to determine suitability and if desired results are achievable with this product. Before sealing, surface should be thoroughly cleaned and prepared with Surebond Cleaners. For spot cleaning, use S.R.B. and/or Oil Extractor before cleaning the surface overall with SureClean. Use Efflo Off for efflorescence cleaning and SureStrip to remove previously applied sealer, other than SB-6000. Thoroughly rinse all cleaner residue from the surface. If installing joint sand/polymeric sand, install on a dry surface prior to sealing.

Prior to Sealing: Use a leaf blower to remove dust, debris and fine sand particles from the surface. Cover/protect nearby landscape, vehicles, and buildings from overspray during application.

APPLICATION INFORMATION:

Apply when day and night temperatures are between 40°F - 95°F. Maximum surface temperature should not exceed 120°F. Allow surface to dry for a minimum of 24 hours after cleaning, polymeric sand activation and/or rain before sealer application. Avoid windy conditions to keep sealer spray from drifting. NO pre-blending or mixing required. DO NOT DILUTE. It is recommended to apply two coats of SB-6000 following coverage guidelines. Excessive applications may decrease breathability and/or cause surface to become slippery. Some surfaces may require an anti-slip additive to increase friction.

COVERAGE PER GALLON:

APPLICATION	SQ FEET	SQ METERS
Pavers & Other Hardscape Surfaces	100-200	9.3-18.6
Concrete	150-250	13.9-23.2
Retaining Walls & Other Vertical Surfaces	100-200	9.3-18.6

Coverage based on single coat. Two coats of SB-6000 are recommended. Second coat is estimated between 200 - 300 sf per gallon (18.6—27.9 m/g). Actual coverage may vary depending on type, age, condition, porosity of the surface, application method and other local conditions such as temperature & humidity.

Application Tools: low-pressure high-volume sprayer, slit foam roller

SB-6000 APPLICATION INSTRUCTIONS



Page 2

APPLICATION INFORMATION: (CONTINUED)

Spray & Back-Roll Application: Use coverage rate for your specific surface. Hold sprayer nozzle perpendicular to the surface, spray and overlap each spray pass. Before sealer dries, back-roll surface with a foam roller to eliminate any pooling and to even out the sealer. Once the first coat is dry to the touch (approximately 60 minutes – affected by humidity and temperature), apply a light second coat at a right angle to the first coat for more uniform coverage. Before sealer dries, back-roll surface with a foam roller to eliminate any pooling and to even out the sealer. Depending on environmental conditions, a light reapplication may be required every 6 months to maintain desired effect.

NOTE: Application of this product is out of the control of SEK-Surebond. Application steps should be followed completely and accurately. Should a problem occur with this product, SEK-Surebond limits liability to product replacement only. Buyer assumes all risk and liability resulting from the use or misuse of this product.

DRY TIME:

Surface will be dry to the touch within 60 minutes assuming 65-85°F at 50% relative humidity. Low surface or air temperature and or high relative humidity will extend dry times. Protect the surface from dust, rain, condensation and traffic while drying. Area can be open to foot & vehicular traffic in 24 hours depending on site conditions. Full cure in 7 days under normal conditions.

CLEAN UP: For tools and equipment, clean with soap and water before product is allowed to dry.

For complete & up to date information on SB-6000, refer to the technical data sheet found on www.sek.us.com.